

AOT12N50/AOB12N50/AOTF12N50 500V, 12A N-Channel MOSFET

General Description Product Summary 600V@150℃ The AOT12N50 & AOB12N50 & AOTF12N50 have been V_{DS} fabricated using an advanced high voltage MOSFET I_D (at V_{GS}=10V) 12A process that is designed to deliver high levels of R_{DS(ON)} (at V_{GS}=10V) < 0.52Ω performance and robustness in popular AC-DC applications.By providing low R_{DS(on)}, C_{iss} and C_{rss} along with guaranteed avalanche capability these parts can be adopted quickly into new and existing offline power supply designs. 100% UIS Tested 100% R_g Tested For Halogen Free add "L" suffix to part number: AOT12N50L & AOTF12N50L & AOB12N50L **Top View** TO-263 D²PAK D TO-220 TO-220F D ς D D G AOTF12N50 AOT12N50 AOB12N50 Absolute Maximum Ratings T_A=25°C unless otherwise noted AOT12N50/AOB12N50 AOTF12N50 Units Parameter Symbol Drain-Source Voltage v V_{DS} 500 V Gate-Source Voltage V_{GS} ±30 T_C=25°C 12 12* Continuous Drain I_D T_C=100°C 8.4 8.4* Current А Pulsed Drain Current C 48 I_{DM} Avalanche Current ^C 5.5 А I_{AR} Repetitive avalanche energy c 454 E_{AR} mJ Single plused avalanche energy 908 E_{AS} mJ MOSFET dv/dt ruggedness 40 dv/dt V/ns Peak diode recovery dv/dt 5 T_c=25°C W 250 50 PD Power Dissipation ^B Derate above 25°C 0.4 W/ °C 2 Junction and Storage Temperature Range -55 to 150 °C T_J, T_{STG} Maximum lead temperature for soldering purpose, 1/8" from case for 5 seconds 300 °C T₁ Thermal Characteristics AOT12N50/AOB12N50 AOTF12N50 Units Parameter Symbol Maximum Junction-to-Ambient A,D $\mathsf{R}_{\theta JA}$ °C/W 65 65 Maximum Case-to-sink A $R_{\theta CS}$ 0.5 °C/W °C/W Maximum Junction-to-Case 2.5 $R_{\theta JC}$ 0.5

* Drain current limited by maximum junction temperature.



Electrical Characteristics (T_J=25°C unless otherwise noted)

Symbol	Parameter	Conditions	Min	Тур	Мах	Units
STATIC I	PARAMETERS					
BV _{DSS}	Drain-Source Breakdown Voltage	I _D =250μA, V _{GS} =0V, T _J =25°C	500			
DVDSS	Dialit-Source Breakdowit Voltage	I_{D} =250µA, V_{GS} =0V, T_{J} =150°C		600		V
BV _{DSS} /∆TJ	Breakdown Voltage Temperature Coefficient	I _D =250μΑ, V _{GS} =0V		0.54		V/°C
	Zara Cata Maltaga Drain Currant	V _{DS} =500V, V _{GS} =0V			1	
IDSS	Zero Gate Voltage Drain Current	V _{DS} =400V, T _J =125°C			10	μA
I _{GSS}	Gate-Body leakage current	V _{DS} =0V, V _{GS} =±30V			±100	nA
V _{GS(th)}	Gate Threshold Voltage	V _{DS} =5V Ι _D =250μΑ	3.3	3.9	4.5	V
R _{DS(ON)}	Static Drain-Source On-Resistance	V _{GS} =10V, I _D =6A		0.36	0.52	Ω
g _{FS}	Forward Transconductance	V _{DS} =40V, I _D =6A		16		S
V _{SD}	Diode Forward Voltage	I _S =1A,V _{GS} =0V		0.72	1	V
I _S	Maximum Body-Diode Continuous Current				12	Α
I _{SM}	Maximum Body-Diode Pulsed Current			48	Α	
DYNAMI	C PARAMETERS					
C _{iss}	Input Capacitance		1089	1361	1633	pF
C _{oss}	Output Capacitance	V _{GS} =0V, V _{DS} =25V, f=1MHz	134	167	200	pF
C _{rss}	Reverse Transfer Capacitance		10	12.6	15	pF
R _g	Gate resistance	V _{GS} =0V, V _{DS} =0V, f=1MHz	1.8	3.6	5.4	Ω
SWITCHI	ING PARAMETERS					
Qg	Total Gate Charge			30.7	37	nC
Q _{gs}	Gate Source Charge	V _{GS} =10V, V _{DS} =400V, I _D =12A		7.6	9	nC
Q_{gd}	Gate Drain Charge			13.0	16	nC
t _{D(on)}	Turn-On DelayTime			29	35	ns
t _r	Turn-On Rise Time	V _{GS} =10V, V _{DS} =250V, I _D =12A,		69	83	ns
t _{D(off)}	Turn-Off DelayTime	$R_{G}=25\Omega$		82	98	ns
t _f	Turn-Off Fall Time			55.5	67	ns
t _{rr}	Body Diode Reverse Recovery Time	I _F =12A,dI/dt=100A/μs,V _{DS} =100V		231	277	ns
Q _{rr}	Body Diode Reverse Recovery Charge	e I _F =12A,dI/dt=100A/μs,V _{DS} =100V		2.82	3.4	μC

A. The value of R $_{_{\rm \theta JA}}$ is measured with the device in a still air environment with T $_{\rm A}$ =25 $^\circ\,$ C.

B. The power dissipation P_D is based on T_{J(MAX)}=150° C, using junction-to-case thermal resistance, and is more useful in setting the upper dissipation limit for cases where additional heatsinking is used.
 C. Repetitive rating, pulse width limited by junction temperature T_{J(MAX)}=150° C, Ratings are based on low frequency and duty cycles to keep initial

T_J =25° C.

D. The R_{eVA} is the sum of the thermal impedence from junction to case R_{eVC} and case to ambient.
E. The static characteristics in Figures 1 to 6 are obtained using <300 µs pulses, duty cycle 0.5% max.
F. These curves are based on the junction-to-case thermal impedence which is measured with the device mounted to a large heatsink, assuming a maximum junction temperature of $T_{J(MAX)}$ =150° C. The SOA curve provides a single pulse rating. G. L=60mH, I_{AS}=5.5A, V_{DD}=150V, R_G=25 Ω , Starting T_J=25° C

THIS PRODUCT HAS BEEN DESIGNED AND QUALIFIED FOR THE CONSUMER MARKET. APPLICATIONS OR USES AS CRITICAL COMPONENTS IN LIFE SUPPORT DEVICES OR SYSTEMS ARE NOT AUTHORIZED. AOS DOES NOT ASSUME ANY LIABILITY ARISING OUT OF SUCH APPLICATIONS OR USES OF ITS PRODUCTS. AOS RESERVES THE RIGHT TO IMPROVE PRODUCT DESIGN, FUNCTIONS AND RELIABILITY WITHOUT NOTICE.



TYPICAL ELECTRICAL AND THERMAL CHARACTERISTICS







Figure 5: Break Down vs. Junction Temperature






TYPICAL ELECTRICAL AND THERMAL CHARACTERISTICS












Figure 10: Maximum Forward Biased Safe Operating Area for AOTF12N50 (Note F)




I_b (Amps)



TYPICAL ELECTRICAL AND THERMAL CHARACTERISTICS












Gate Charge Test Circuit & Waveform







Resistive Switching Test Circuit & Waveforms





Unclamped Inductive Switching (UIS) Test Circuit & Waveforms





Diode Recovery Test Circuit & Waveforms









Document No.	PD-00650
Version	А
Title	AOT12N50 Marking Description

TO220 PACKAGE MARKING DESCRIPTION





Standard product

NOTE: LOGO - AOS Logo T12N50 - Part number code - Fab code - Assembly location code - Year code W - Week code


L&T	- Assembly lot code
-----	---------------------

 \mathbf{F}


Α Y

I	PART NO.	DESCRIPTION	CODE
I	AOT12N50	Standard product	T12N50
A	OT12N50L	Green product	<u>T12N50</u>

Green product



RECOMMENDATION OF HOLE PATTERN



UNIT: mm


NOTE

- 1. PACKAGE BODY SIZES EXCLUDE MOLD FLASH AND GATE BURRS.
- MOLD FLASH SHOULD BE LESS THAN 6 MIL.
- 2. TOLERANCE 0.100 MILLIMETERS UNLESS OTHERWISE SPECIFIED.
- 3. CONTROLLING DIMENSION IS MILLIMETER.
- CONVERTED INCH DIMENSIONS ARE NOT NECESSARILY EXACT.

	DIMENS	ions in Mili	IMETERS	DIME	NSIONS IN I	NCHES
SYMBOLS	MIN	NDM	MAX	MIN	NDM	MAX
A	4.30	4.45	4.72	0.169	0.175	0.186
A1	1.15	1.27	1.40	0.045	0.050	0.055
A2	2.20	2.67	2.90	0.087	0.105	0.114
b	0.69	0.81	0.95	0.027	0.032	0.037
b2	1.17	1.37	1.45	0.046	0.050	0.068
с	0.36	0.38	0.60	0.014	0.015	0.024
D	14.50	15.44	15.80	0.571	0.608	0.622
D1	8.59	9.14	9.65	0.338	0.360	0.380
D2	11.43	11.73	12.48	0.450	0.462	0.491
e	2.54 BSC			().100 BSC	<u>,</u>
E	9.66	10.03	10.54	0.380	0.395	0.415
E1	6.22			0.245		
H1	6.10	6.30	6.50	0.240	0.248	0.256
L	12.27	12.82	14.27	0.483	0.505	0.562
L1	2.47		3.90	0.097		0.154
L2			16.70			0.657
Q	2.59	2.74	2.89	0.102	0.108	0.114
ØР	3.50	3.84	3.89	0.138	0.151	0.153
Q1	2.70		2.90	0.106		0.114



TO220/TO262 TUBE



- 1. TUBE
 - MATERIAL : P.V.C
 - COLOR : TRANSPARENCY, RED, YELLOW
 - MARKING #A : 6 MONTHS, BLACK COLOR LETTER STYLE : Arial
 - CAMBAR : 1.5 MAX
- 2. PIN
 - COLOR : GREEN (ONE PIN MUST BE INSERTED IN LEFT-SIDE OF " ANTISTATIC~" AND ANOTHER PIN IS FREE.)
- 3. ALL UNSPECIFICATED SPECIFICATIONS FOLLOW TUBE GENERAL SPEC. UNSPECIFICATED TOLERANCE ±0.2
- 4. PACKING Q'TY :

PKG	Q'TY(PCS)
TO220/ TO262	50



AOS Semiconductor Reliability Report

HVMOS Family Report, rev A

ALPHA & OMEGA Semiconductor, Inc

www.aosmd.com

AOS Reliability Report



This report applies for high voltage (900V/700V/650V/600V/500V) products assembled in following packages TO220 (F)/TO262 (F)/TO263/TO252 /TO251 (A).

"Commitment to Excellence at Quality & Reliability!"

To achieve this vision, AOS continuously strive for the excellence in design, manufacturing, reliability and proactively response to the customer's feedback.

AOS ensures that all the product quality and reliability exceed the customer's expectation by constantly assessing any potential risk, identifying cause of the suspected failures, driving corrective actions and developing prevention plan within the committed time through the continuously improvement.

This AOS product reliability report summarizes AOS Product Reliability result. The published product reliability data combines the results from new product Qualification Test Plan and routine Reliability Program activities. Accelerated environmental tests are performed on a specific sample size, and then followed by electrical test at end point. The released product will be categorized by the process family and be monitored on a quarterly basis for continuously improving the product quality. Table 1 lists the generic reliability qualification requirements and conditions:

Test Item	Test Condition	Time Point	Sample size	Acc/Reject
НТСВ	Temp = 150°c, Vgs=100% of Vgsmax	168 / 500 hrs 1000 hrs	77 pcs / lot	0/1
HTRB	Temp = 150°C, Vds=80% of Vdsmax	168 / 500 hrs 1000 hrs	77 pcs / lot	0/1
Solder reflow precondition	168hr 85°c /85%RH + 3 cycle reflow @250°c (MSL level 1)	-	The sum of PCT ,TC and HAST	0/1
HAST	130 +/- 2°C, 85%RH, 33.3 psi, Vgs = 80% of Vgs max	100 hrs	55 pcs / lot	0/1
Pressure Pot	121°C , 29.7psi, 100%RH	96 hrs	77 pcs / lot	0/1
Temperature Cycle	-65°C to 150°C, air to air,	250 / 500 cycles	77 pcs / lot	0/1
Power Cycle	Δ Tj = 125 °C	4286 cycles	77 pcs / lot	0/1

Table 1: AOS Generic Reliability Qualification Requirements



High Temperature Gate Bias (HTGB) & High Temperature Reverse Bias (HTRB)

HTGB burn-in stress is used to stress gate oxide at the elevated temperature environment hence any of the gate oxide integrity issue can be identified. HTRB burn-in stress is used to verify junction degradation under the maximum operation temperature.

Through HTGB & HTRB B/I stress test, the device lifetime in field operation & long term device level reliability can be determined. FIT rate is calculated by applying the Arrhenius equation with the activation energy of 0.7Ev and 60% of upper confidence level at 55 deg C operating conditions.

Solder reflow precondition (pre-con)

Solder reflow precondition is the test that simulates shipment and storage of package in under uncontrollable environment. Precondition is the pre-requirement for the mechanical related reliability tests (such as Temperature Cycle, Pressure Pot and High Acceleration Stress TEST (HAST). The routine of the test are: parts will be soaked in moisture then bake in pressure pot, or being placed into 85% RH, 85 deg C environment for 168 hrs. Then they will be run through a solder reflow oven with temperature at 260°C+/- 5°C or 250°C+/- 5°C (depending on package thickness and volume). The test condition totally complies with MSL level 1. Pre-condition is a test that is detected package delamination, lifted bond wire issue.

Temperature Cycling (TC)

Temperature cycling test is to evaluate the mechanical integrity of the package and the interaction between the die and the package. This is an air to air test at temperature range from -65°C/150°C and stress duration is from 250 cycles to 500 cycles.

Pressure Pot (PCT)

PCT test is the test that measures the ability of the device withstand to moisture and contaminant environment. The test is done under enclosed chamber with the condition 121°C 15+/- 1PSIG, 100%RH and stress duration is 96 hrs.

High Acceleration Stress Test (HAST)

High acceleration stress test is to stress the devices under high humidity, high pressure environment under DC bias condition. If ionic contamination involved, the corrosion from metal layer can be accelerated by the HAST stress condition.

Power Cycle

The power cycle test is performed to determine that the ability of a device to withstand alternate exposures at high and low junction temperature extremes with operating biases periodically applied and removed. It is intended to simulate worst case conditions encountered in typical application.

The following tables summarize the qualification results based on the device/process families and the package types, respectively.



Summary of AOS High Voltage MOSFET product with TO220 (F)/TO262 (F)/TO263/TO252 /TO251 (A) package Qualification Results

Table 2 Product Family

Voltage	Device No.	Package
900V	AOTFXXN90	TO220F
700)/	AOTFXXN70	TO220F
700V	AOTXXN70	TO220
	AOTFXXN65	TO220F
650V	AOTXXN65	TO220
650 V	AOWFXXN65	TO262F
	AOWXXN65	TO262
	AOTFXXN60	TO-220F
	AOTXXN60	TO-220
	AOWFXXN60	TO262F
600V	AOWXXN60	TO262
600 V	AOBXXN60(L)	TO263
	AODXXN60	TO252
	AOUXXN60	TO251
	AOIXXN60	TO251A
	AOWFXXN50	TO262F
	AOWXXN50	TO262
	AOTFXXN50	TO-220F
500∨	AOTXXN50	TO-220
	AOBXXN50	TO263
	AODXXN50	TO252
	AOUXXN50	TO251

Note: Letter 'XX' is 1 or 2 digital which stands for Id (Continuous Drain current at 25°C) of this product. For example, AOTF14N50, '14' means Id of this product is 14A.



Table 3 Reliability Test and Package test Result:

Test Item	Test Condition	Time Point	Total Sample size	Number of failure
нтдв	Temp = 150°c,Vgs=100% of Vgsmax	168 / 500 hrs 1000 hrs	2541	0
HTRB	Temp = 150°C, Vds=80% of Vdsmax	168 / 500 hrs 1000 hrs	2464	0
Solder reflow precondition			3839	0
HAST	ST 130 +/- 2°C , 85%RH, 33.3 psi, Vgs = 80% of Vgs max		605	0
Pressure Pot	121°C,29.7psi, 100%RH	96 hrs 1540		0
Temperature Cycle			2002	0
Power Cycle	Power Cycle $\Delta Tj=125^{\circ}C$		231	0
Solder dunk 260°C, 10secs		3 cycles	77	0



Reliability Evaluation:

FIT rate (per billion): 1.74 MTTF = 65789 years

The presentation of FIT rate for the individual product reliability is restricted by the actual burn-in sample size of the selected product. Failure Rate Determination is based on JEDEC Standard JESD 85. FIT means one failure per billion hours.

Failure Rate (FIT) = $\text{Chi}^2 \times 10^9$ / [2 (N) (H) (Af)] = 1.83 × 10^9 / [2 (2541) (168) (258) +2(1694) (500) (258) + 2(770) (1000) (258)] = 1.74 MTTF = 10^9 / FIT = 5.76 × 10^8 hrs = 65789 years

WITE = 10° / FIT = 5.76 X 10 mrs = 65789 years

Chi² = Chi Squared Distribution, determined by the number of failures and confidence interval **N** = Total Number of units from HTRB and HTGB tests **H** = Duration of HTRB/HTGB testing **Af** = Acceleration Factor from Test to Use Conditions (Ea = 0.7eV and Tuse = 55°C) Acceleration Factor [**Af**] = **Exp** [Ea / **k** (1/Tj u - 1/Tj s]

Acceleration Factor ratio list:

	55 deg C	70 deg C	85 deg C	100 deg C	115 deg C	130 deg C	150 deg C
Af	258	87	32	13	5.64	2.59	1

Tj s = Stressed junction temperature in degree (Kelvin), K = C+273.16

Tj u =The use junction temperature in degree (Kelvin), K = C+273.16

 \mathbf{k} = Boltzmann's constant, 8.617164 X 10⁻⁵eV / K